



Synthesis of Silver Nanoparticles from *Buteamonosperma* for Anticancer Activity on MCF 7 Human Breast Cancer Cell Line.

A.M. Patil¹, S. Das¹, HL Raghavendra¹, B.S. Honde², G.B. Janvale³

¹Centre for Biotechnology, Pravara Institute of Medical sciences (DU), Loni, Dist. Ahmednagar, (MS) India

²Department of Pharmaceutical Chemistry, S.V.N.H.T.S College of B. Pharmacy, Rahuri Factory, Rahuri, Ahmednagar, (MS) India

³Department of Bioinformatics, CABT, Madadgaon, (MPKV Rahuri) Ahmednagar, (MS), India

Abstract:

In this research, silver nanoparticles were synthesized from *Buteamonosperma* for *in vitro* cytotoxicity efficacy against MCF-7 cells. Silver nanoparticles are deemed the most positive, considering their strong volume surface region, and are of concern for study because of the improved microbial tolerance to antibiotics and medicines. Therefore, green synthesis of nanoparticles of silver using biomolecules derived from various plant sources in the form of extracts can be applied for the screening of different diseases which trigger microorganisms and for the physical and biological characterization of plant-derived silver nanoparticles. The experiment involved the green synthesis of silver nanoparticles (AgNPs) from *Butea monosperma* leaf extract. Biosynthesized *Butea monosperma*-AgNPs were characterized by UV-visible spectroscopy, Fourier-transform infrared (FTIR) spectroscopy and scanning electron microscopy (SEM). The intensity of peak broad range 200-800nm in UV-vis spectra, EDS test. The SEM shows the actual size of the nanoparticles. The MTT assays were carried out for cytotoxicity of various concentrations of biosynthesized silver nanoparticles. The biosynthesized silver nanoparticles showed a significant anticancer activity against both MCF-7. Our study thus revealed an excellent application of green synthesized silver nanoparticles. At the Concentration 80µg/ml, Sample Code A, B, C, D samples showed good percent inhibition MCF7 cell line as compared to standard drug. The study also suggested the potential therapeutic use of these nanoparticles in cancer study.

Keywords: *Butea monosperma*, UV-visible spectroscopy, Fourier-transform infrared (FTIR) spectroscopy and Scanning Electron Microscopy (SEM), Silver nanoparticles, Anticancer activities, MCF 7 human breast cancer cell line, MTT assay.

1. Review of Literature

Cancer is an abnormal uncontrollable cell cycle disease characterized by the rapid proliferation of normal cells. Cancer has been ranked as the second leading cause of death all over the world, preceded only by cardiovascular diseases. Metals such as metals and metal oxides, silicates, non-oxide ceramics, polymers, organic materials, biomass and biomolecules may be used for producing nanoparticles. In various morphologies, nanoparticles occur, including balls, cylinders, platelets, tubes etc. Inorganic nanoparticles such as golden and silver metal nanoparticles have superior material properties with mechanical flexibility, with broad availability, comprehensive mobility, strong compatibility, selective therapeutic products and regulated drug release capabilities (Xu *et al.*, 2006). For the synthesizing and stabilisation of silver nanoparticles, many physical, chemical and biological methods were used (Senapatiet *al.*, 2005). The word biofilm has been

used to refer to the thin coated condensations of microbes (for example bacteria, fungi, protozoa, etc.) which can appear in different types of surface structures. Antifungal performance may be calculated by means of well diffused methods on various fungal strains. (Chitte *et al.*,2016) Free floating bacteria, classified as planktonic microorganisms in an aqueous climate, are a requirement for the development of biofilms. Thus, such films may be formed on every organic or inorganic substratum where planktonic microorganisms prevail in a water solution (Choudhary *et al.*, 2012). Because of its unusual physical and chemical properties, silver nanoparticles (AgNPs) are progressively being used in numerous fields, including medical, fruit, patient treatment, consumption and industrial uses. This involves visual, electronic, thermal, heavy electrical and biological characteristics (Gurunathan *et al.* 2015). Because of its unusual properties, it has been used for many applications in the medicinal, food processing, surgical, orthopedic, medication distribution, anticancer industries, as well as for numerous applications such as non-bacterial agents, automotive, domestic and health goods, electronic products, medical equipment jackets, optical sensors and cosmetics AgNPs have been widely used lately in numerous textiles, keyboards, wound dressings and biomedical instruments. The nanosized metallic particles are peculiar and, because of their surface to volume ratio, can greatly alter physical, chemical and biological properties; thus, nanoparticles have been used for different purposes. In order to satisfy the AgNPs criterion, different methods for synthesis have been introduced. In general, current approaches of physics and chemistry appear rather costly and risky. It is important to notice the high yield, solubility and high stability of biologically prepared AgNPs (Gurunathan *et al.*, 2015). Biological methods for AgNPs seem simplistic, quick, nontoxic, reliable and green among. A range of analytical methods are used, including UV spectroscopy, X-ray diffraction (XRD), Fourier transform infrared spectroscopy (FTIR), X-ray photoelectron spectroscopy (XPS), DLS scanning, SEM, transmission electron microscope (TEM), atomic force microscopy (AFM) (K Venugopal *et al.*,2017) (Raju Vivek, *et al.*,2012),(V. Kathiravan *et al.*,2014),(Shahnaz Majeed, *et al.*,2019),(Sabina Yeasmin *et al.*,2017),(R.M. Gengan *et al.*, 2013),(R.R. Remya *et al.*, 2015). Several competent books and studies have identified different styles of methodological methods for characterising AgNPs. A highly effective and accurate technique for the primary characterization of synthesised nanoparticles used for tracking the production and stabilisation of AgNPs is UV-Visible Spectroscopy. (Sastri *et al.*, 1998).

2. Materials and Methods

2.1 Sample preparation: The young and disease-free leaves of *Butea monosperma* were selected.

Drying of leaves:- Leaf samples were dried in room temperature for more than two weeks, so that they may be converted into fine powder.

Preparation of fine powder: after proper drying of leaves, thick mid ribs of the leaves was removed, dried leaves were grinded into fine powder using a grinder.

Preparation of extracts: aqueous extracts using distilled water, 50% ethanol, 50% methanol & 50% acetone were prepared.

2.2 Synthesis of Silver Nanoparticles from *Butea monosperma* extracts:

AgNPs were synthesized by the following method. 10mM AgNO₃: plant extracts in different solvent in 9:1 ratio in a reagent bottle mixed thoroughly, forming a uniform mixture. The mixture was then rested at room temperature for 24 hours at 37°C, with continuous monitoring. After about few minutes, the mixture was observed to start changing from pale green to yellowish brown. After about 24 hours, the mixture had completely changed colour to brown in all solvents. This color change is visual evidence of formation of AgNPs. (Kasthuri *et al.*, 2009).

2.3 Characterization of silver nanoparticles.

For determination of the time point of maximum production of silver nanoparticles, the absorption spectra of the samples were taken 200–800 nm using a UV–vis spectrophotometer. The silver nanoparticles were synthesized by novel green chemical route. The nanoparticles were characterized by UV- spectral analysis, SEM -EDAX analysis (Scanning Electron Microscopy) was performed for studying the surface morphology & to predict the size of the nanoparticle. Also, FTIR analysis was conducted for identifying the presence of functional groups. (Anuja *et al.* 2020)

Anticancer Activity:

1. CO2 Incubator- ThermoFisher,USP
2. Multimode micro plate reader- Bene SpheraE21 Avantor USP.
3. Refrigerated centrifuge- Eppendorf Germany.
4. Cell : MCF-7 (Human breast cancer cell line) NCCS Pune.
5. MTT.(3-(4,5-dimethyl thiazol-2-yl)-2,5-diphenyltetrazoliumbromide)).
6. Fetabovineserum (Gibco,Invitrogen) (CatNo.-10270106)
7. Trypsin.
8. Penicillin.
9. DMEM With high glucose (CatNo.-11965-092).
10. Antibiotic- Antimycotic 100X solution

(Thermo fisher scientific)- (CatNo.-1524006)

Media:DMEM with high glucose (Cat No-11965-092), FBS (Gibco, Invitrogen)Cat No -10270106 Antibiotic – Antimycotic 100X solution (Thermo fisher Scientific)-Cat No-15240062 Activity: MTT Assay: Experimental procedure:

- 1) Cells were incubated at a concentration of 1×10^4 cells/ml in culture medium for 24 h at 37°C and 5% CO₂.
- 2) Cells were seeded at a concentration (70µl) 104 cells/well in 100 µl culture medium and 100µl sample of Sample A to D in (10, 40.80 µg/ml) into micro plates respectively (tissue culture grade, and 96 wells).
- 3) Control wells were incubated with DMSO (0.2% in PBS) and cell line. All samples were incubated in triplicate. Controls were maintained to determine the control cell survival and the percentage of live cells after culture.
- 4) Cell cultures were incubated for 24 h at 37°C and 5% CO₂ in CO₂ incubator (Thermo scientific BB150)
- 5) After incubation, the medium was completely removed and Added 20 µl of MTT reagent (5mg/min PBS).
- 6) After addition of MTT, cells incubated for 4 hrs at 37°C in CO₂ incubator.
- 7) Observed the wells for formazan crystal formation under microscope. The yellowish MTT was reduced to dark coloured formazan by viable cells only.
- 8) After removing the medium completely. Added 200µl of DMSO (kept for 10 min) and incubate at 37°C (wrapped with aluminum foil).

Result

3.1 The detailed study on biosynthesis of silver nanoparticles by natural *Butea monosperma* extracts such It was observed that the color of the solution turned from yellow to bright yellow and then to dark brown after 1, 24 and 48 h of the reaction, which indicated the formation of silver nanoparticles (fig 1).

3.2 The formation and stability of the reduced silver nanoparticles in the colloidal solution was monitored by UV–vis spectrophotometer analysis. The UV–vis spectra show maximum absorbance at 420 nm, which increased with time of incubation of silver nitrate with the plants extract. The curve shows increased absorbance in various time intervals (1 h, 24 h and 48 h) and the peaks were noticed at 420 nm corresponding to the surface plasmon resonance of silver nanoparticles. The observation indicated that the reduction of the Ag⁺ ions took place extracellularly. It is reported earlier that absorbance at around 430 nm for silver is a characteristic of these novel metal particles (Nestor *et al.*, 2008). The synthesis of AgNPs from the ethanolic, aqueous, methanol & acetone extract of leaves of *Butea monosperma* was further confirmed by ultraviolet - visible spectroscopy (UV/VIS) in the range of between 200 nm to 800 nm and solvents were used as a blank. The spectrum has a maximum absorption peak at a which is reported to have an absorption maximum of between about 400nm to about 450nm. The presence of the maximum peak absorption peak at 400nm to about 450nm is therefore an indication and confirmation that the AgNPs were present. (Fig 1)




Fig.1. a) Synthesis of nanoparticles using *Butea monosperma* b) and c) presence of the maximum peak absorption peak at 400nm to about 450nm

3.3 Fourier Transform Infra-Red Spectrometer (Equipped With ATR) Model Tensor 600 Bruker. As seen in figure given below, FTIR spectra of all samples shows similar pattern.




Fig. 2. FTIR spectra of all four solvents of *Butea monosperma* synthesized Silver AgNPs

FTIR spectra depicts bands at $\sim 3200-3300$ corresponding to alcoholic O-H stretching, bands at ~ 1620 corresponds to; where as small band at ~ 1100 is corresponds to alcoholic C-O bond, metallic silver bond is seen at ~ 450 cm^{-1} . Fig 2 where A-water, B Ethanol, C methanol & D acetone solvents respectively.

3.4) Field Emission Scanning Electron Microscopy (Fe-SEM) & Energy Dispersive X-Ray spectroscopy (EDS) Analysis. Thin film of the as obtained sample was prepared on cleaned glass plate using drop casting technique. This film is dried under Infra-Red lamp at room temperature. As depicted in electron micrographs, sample consist of clusters of ultrafine nanoparticles of size $\sim 40-75$ nm. Fig 4 To confirm the composition of the sample, EDS analysis is done. As seen from the spectra depicted in chart1, Sample prominently consist of Ag along with S, P, O and Si.




Fig 3 Field Emission Scanning Electron Microscopy (Fe-SEM)

Table 1: Elemental composition of as synthesized sample

Element	Atomic No	A	B	C	D
Carbon	6	23.81	20.64	19.07	22.53
Aluminum	13	10.18	ND	ND	ND
Silver	47	47.10	45.49	44.70	45.60
Sulfur	16	5.20	ND	ND	ND
Phosphorus	15	1.50	ND	ND	ND
Silicon	14	1.23	ND	ND	ND
Oxygen	8	10.98	9.91	36.24	31.88

Table 2: Effects of *Buteamonosperma*AgNPs solutions against MCF7 (human breast cancer cell line) by MTT assay.

Sr. No.	Sample	Concentration (µg/ml)	OD	% Inhibition
1	Control		1.275	
2	Std. 5FU	10	0.965	75.68
		40	0.736	57.72
		80	1.123	96.00
3	A	10	0.658	51.00
		40	0.756	59.29
		80	0.822	64.47
4	B	10	1.003	78.66
		40	1.118	87.68
		80	1.273	99.03
5	C	10	1.223	74.90
		40	1.257	76.70
		80	1.273	88.94
6	D	10		95.92




Fig.3: At the Concentration 80µg/ml, sample Code A, B, C, D samples showed good percent inhibition MCF7cell line as compared to standard drug.

Conclusion:

In this study, different temperatures were used for silver nanoparticle biosynthesized by using *Buteamonosperma* extract. The greatest Plasmon resonance was acquired at 60 °C previously, improved the procedure parameters for incorporating AgNPs by utilizing aqueous extracts of *Buteamonosperma*. UV–Vis spectroscopy and FT-IR analysis confirmed the formation of the silver nanoparticles. The size of AgNPs was confirmed by TEM analysis, which illustrates that AgNPs were spherical in shape with size ranging from 5 to 40 nm. Synthesized AgNPs appeared polydispersed and well scattered. The synthesized silver nanoparticles and *Buteamonosperma* extracts were compared and showed promising cytotoxicity activity against MCF-7 cell line. From the study, it can be concluded that the silver nanoparticles synthesized using plant, possess high cytotoxicity activity against cell lines which suggests the potential therapeutic use of these nanoparticles. At the Concentration 80 µg/ml, Sample Code A, B, C, D samples showed good percent inhibition MCF7 cell line as compared to standard drug.

References:

1. A. Y. Hwang and J. G. Gums, (2016); “The emergence and evolution of antimicrobial resistance: Impact on a global scale,” *Bioorganic & Medicinal Chemistry*, vol. 24, no. 24, pp. 6440–6445.
2. Arangasamy Leela and Munusamy Vivekanandan (2008): Tapping the unexploited plant resources for the synthesis of silver nanoparticles, *African Journal Of Biotechnology* Vol.7 (17):3162-65.
3. Chandraker SK. A review on endangered plant of Chhattisgarh: *Buteamonosperma* (Lam.) (Parsa). *IJPRBS* 2014; 3(3): 165- 177.
4. Chi-Yu Chena, Yen-Hsu Chen, Po-Liang L, Wei-Ru Linae, *Proteus mirabilis* urinary tract infection and bacteremia: Risk factors, clinical presentation, and outcomes. , *Journal of Microbiology, Immunology and Infection* Volume 45, Issue 3, June 2012, Pages 228-236
5. Gajbhiye, M.; Kesharwani, J.; Ingle, A.; Gade, A.; Rai, M. Fungus-mediated synthesis of silver nanoparticles and their activity against pathogenic fungi in combination with fluconazole. *Nanomedicine* 2009, 5, 382–386.
6. Gangurde Anuja Suklall, Daspute Abhijit Arun2, Akash Pansande1, .Wagh Sopan Ganpatrao3, Patil Akshay4 and Priyanka Kharpude1 Effect of pomegranate (*Punicagranatum*) peel extract on improving vase-life of cut carnation (*Dianthus caryophyllus*) *Current Horticulture* 8(2): 47–50, July–December 2020
7. Guo, D.; Zhu, L.; Huang, Z.; Zhou, H.; Ge, Y.; Ma, W.; Wu, J.; Zhang, X.; Zhou, X.; Zhang, Y.; et al. Anti-leukemia activity of PVP-coated silver nanoparticles via generation of reactive oxygen species and release of silver ions. *Biomaterials* 2013, 34, 7884–7894.
8. K Venugopal, H A Rather, K Rajagopal, M P Shanthi, K Sheriff, M Illiyas, R A Rather, E Manikandan, S Uvarajan, M Bhaskar, M Maaza, Synthesis of silver nanoparticles (Ag NPs) for anticancer activities (MCF 7 breast and A549 lung cell lines) of the crude extract of *Syzygium aromaticum*, *Journal of Photochemistry and Photobiology B: Biology*, Volume 167, 2017, Pages 282-289, ISSN 1011-1344.
9. Kalishwaralal, K.; Banumathi, E.; Ram Kumar Pandian, S.; Deepak, V.; Muniyandi, J.; Eom, S.H.; Gurunathan, S. Silver nanoparticles inhibit VEGF induced cell proliferation and migration in bovine retinal endothelial cells. *Colloids Surf. B: Biointerfaces* 2009, 73, 51–57.
10. Kasthuri, J., Veerapandian, S., Rajendiran, N., 2009. Biological synthesis of silver and gold nanoparticles using apiin as reducing agent. *Colloids Surf. B: Biointerf.* 68, 55–60
11. Kleinauskas, A.; Rocha, S.; Sahu, S.; Sun, Y.P.; Juzenas, P. Carbon-core silver-shell nanodots as sensitizers for phototherapy and radiotherapy. *Nanotechnology* 2013, 24, 325103.
12. Madhavi A. An Overview of *Buteamonosperma* (Flame of Forest). *WJPPS* 2013; 3(1): 307-319.

13. More BH, Sakharwade SN, Tembhumne SV, Sakarkar DM. Ethnobotany and Ethanopharmacology of *Butea Monosperma* (Lam) Kuntze- A Compressive Review. *Am J PharmTech Res* 2012; 2(5): 138-159.
14. R.M. Gengan, K. Anand, A. Phulukdaree, A. Chuturgoon, A549 lung cell line activity of biosynthesized silver nanoparticles using *Albizia adianthifolia* leaf, *Colloids and Surfaces B: Biointerfaces*, Volume 105, 2013, Pages 87-91, ISSN 0927-7765,
15. R.M.Crooks ,B.I.Lemon,L.Sun,L.K.Yeung,M.Zhao(2001) *Top Curr. Chem*:212:2-135.
16. R.R. Remya, S.R. Radhika Rajasree, L. Aranganathan, T.Y. Suman, An investigation on cytotoxic effect of bioactive AgNPs synthesized using *Cassia fistula* flower extract on breast cancer cell MCF-7, *Biotechnology Reports*, Volume 8, 2015, Pages 110-115, ISSN 2215-017X,
17. Raju Vivek, RamarThangam, KrishnasamyMuthuchelian, PalaniGunasekaran, KrishnasamyKaveri, Soundarapandian Kannan, Green biosynthesis of silver nanoparticles from *Annona squamosa* leaf extract and its in vitro cytotoxic effect on MCF-7 cells, *Process Biochemistry*, Volume 47, Issue 12, 2012, Pages 2405-2410, ISSN 1359-5113.
18. Rennaly de Freitas LIMA, Terezakarlavieira lopes da costa, Ilzamaria de oliveirasousa, Elaine cristinacabral, *Original Research, Microbiology Braz. oral. res.* 32(2018)
19. Sabina Yeasmin, Hemanta Kumar Datta, Sujata Chaudhuri, Debasish Malik, Abhijit Bandyopadhyay, In-vitro anti-cancer activity of shape controlled silver nanoparticles (AgNPs) in various organ specific cell lines, *Journal of Molecular Liquids*, Volume 242, 2017, Pages 757-766, ISSN 0167-7322,
20. Shahnaz Majeed, NurFadlinBintiBakhtiar, Mohammed Danish, M.N. Mohamad Ibrahim, RokiahHashim, Green approach for the biosynthesis of silver nanoparticles and its antibacterial and antitumor effect against osteoblast MG-63 and breast MCF-7 cancer cell lines, *Sustainable Chemistry and Pharmacy*, Volume 12, 2019, 100138, ISSN 2352-5541.
21. Sharma AK, Deshwal N. An Overview: On Phytochemical and Pharmacological Studies of *Butea Monosperma*. *Int J PharmTech Res* 2011; 3(2): 864-871.
22. Sindhia VR, Bairwa R. Plant Review: *Butea monosperma*. *Int J of Pharma and Clinical Res* 2010; 2(2): 90-94. 2 9.
23. Thakkar, K.N.; Mhatre, S.S.; Parikh, R.Y. Biological synthesis of metallic nanoparticles. *Nanomedicine* 2010, 6, 257–262.
24. V. Kathiravan, S. Ravi, S. Ashokkumar, Synthesis of silver nanoparticles from *Melia dubia* leaf extract and their in vitro anticancer activity, *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*, Volume 130, 2014, Pages 116-121, ISSN 1386-1425.
25. V.parashar, R.Parashar ,B.Sharma,A.C.Pandey (2009) *Digest journal of Nanomaterials and Biostructures* 4(1):45-50.