



FORMULATION AND IN VITRO CHARACTERIZATION OF TOPICAL HYDROGEL CONTAINING ANTIMYCOTIC DRUG

¹Shritesh Bhojar, ²Nishan Bobade, ³Mohini Murkute, ⁴Aachal Kolhe, ⁵Hemangi Vaishnav

^{1,3,4,5}PG Student, ²Associate Professor

^{1,2,3,4,5} Department of Pharmaceutics

^{1,2,3,4,5}Vidyabharati College of Pharmacy, Amravati, Maharashtra, India

Abstract: The Hydrogel are three-dimensional, hydrophilic, polymeric network capable of absorbing large amounts of water or biological fluids due to high water content, porosity and soft consistency stimulate natural living tissue, and has rapid absorption rate. The aim of present study is to formulate topical hydrogel containing Luliconazole to treat fungal infections using synthetic gelling agents such as HPMC K4M, and Carbopol-934 evaluated for various parameter. The drug-excipient compatibility studies shows that there is no interaction between drug and selected polymer(s). For present work 3^2 factorial design was selected, two independent variables were selected i.e., Carbopol-934 (X1) & HPMC-K4M (X2) and nine formulations were formulated as per experimental design. The Nine formulation were evaluated for the various parameters and their result were found to be as for pH (6 to 6.9), the viscosity (3130 to 10318) cp, % drug content (95.18 to 98.26), the cumulative % drug release in 8 hours (79.49 to 53.15). The Batch F1 was selected as optimized formulation containing HPMC K4M 1%w/v, Carbopol-934 1%w/v, Methyl Paraben 0.1% w/v, Propyl Paraben 0.05% w/v, Glycerine 1ml and water up to 10ml. and follows zero order kinetic. The optimized batch was found to be stable as per ICH study. It was concluded that problem associated with Luliconazole by oral administration like GIT ulceration can be overcome by topical route of administration of hydrogel

Index Terms - Hydrogel, Luliconazole, HPMC-K4M, Carbopol-934, Topical.

1.INTRODUCTION

The topical route of drug delivery has been utilized to produce local effect for treating skin diseases and produce systemic drug effects. Hydrogels are prepared both in cosmetics and in pharmaceutical preparations. Gels often provide better release of drug substance independent of the water solubility of the drug when compared to creams and ointments. Local application of therapeutic compounds has many advantages over oral and parenteral drug delivery systems. The advantages include ease of application to skin, ability to deliver drugs selectively to a site of local action, elimination of hepatic first-pass metabolism and better patient compliance. Hydrogels are widely used in topical drug delivery systems due to their physical and chemical properties such as controllable and prolonged release of drug. These formulations on contact with the skin forms a semi occlusive film over the skin and release the drug in

controlled manner. Lipophilic drug can cross the Stratum corneum, but rate of diffusion decreases as it enters the more aqueous lower regions of the epidermis. Fungal infections have been divided into superficial and systemic infections.¹⁰ Antifungal drugs are classified according to their chemical structure as azoles, polyenes, allylamines, echinocandins. Luliconazole is an antifungal medication used in the treatment of superficial skin infections such as tinea corporis, tinea pedis and tinea cruris caused by *T. rubrum* and *E. floccosum*. Luliconazole acts by inhibiting enzyme synthesis like lanosterol demethylase and lanosterol demethylase is major ingredient for synthesis of fungal cell. The goal of our research to formulate and evaluate Luliconazole hydrogels for prepared formulations.^[1,2]

2. Methodology

2.1 Materials

Luliconazole was obtained from virupaksha organics limited (Hyderabad), Carbopol-934, HPMC-K4M, Glycerine, Triethanolamine, Methyl Paraben and Propyl Paraben provided by the Vidyabharati college of pharmacy, Amravati, Maharashtra

2.2 Methods

a) Determination of Lambda Max

Stock (100µg/ml) of Luliconazole was prepared in Phosphate buffer pH 7.4. The solution was kept in Quartz cuvette having thickness 10mm. the UV spectrum was in the range of 200-400nm Shimadzu UV- visible spectrophotometer (UV- 1800) at 1cm, slit width. It showed lambda max at 296 nm using spectrophotometer. The procedure was repeated for accuracy at least three times.

b) Standard Calibration Curve of Luliconazole in pH 7.4 Phosphate

Buffer 100mg of Luliconazole pure drug was liquefied in 10 ml of ethanol and made upto 100ml with phosphate buffer pH 7.4 in a volumetric flask. 20-50 µg/ml dilutions were primed with buffer from the stock solution. The absorbance's of the solutions were analysed at 296 nm.

c) FTIR Spectrophotometry

The spectrum was recorded in the wavelength region of 4000 to 400cm⁻¹. A disc sample of the drug and polymer were mixed uniformly and filled into the die cavity and the sample holder and an IR spectrum was recorded using diffuse reflectance FIR spectrophotometer

d) Formulation of Luliconazole Hydrogel: -

For the present work 3² factorial was selected. Two independent variables were selected Carbopol-934 (X1) and HPMC-K4M (X2) and nine formulations formulated as per experimental design. Formulation table by factorial design. All the ingredients were collected according to the formula given in table no 1, Required number of gelling agents such as Carbopol-934 & HPMC-K4M were added in water with constant stirring at 500 rpm for about 2hours. Drug was added to the above mixture. Methyl Paraben & Propyl Paraben were added to it. Final weight was made with water. All the samples were collected to equilibrate for 24 hours at room temperature prior to performing evaluation test Triethanolamine used to Maintain pH of sample^[4]

Table NO.1 Formulation Table by Factorial Design

Formulation Code	Luliconazole(mg)	Carbopol-934(%)	HPMC-K4M (%)	Methyl Paraben (%)	Propyl Paraben (%)	Glycerine (ml)	Water up to (ml)
F1	1	1	1	0.1	0.05	1	10
F2	1	1	1.5	0.1	0.05	1	10
F3	1	1	2	0.1	0.05	1	10
F4	1	1.5	1	0.1	0.05	1	10
F5	1	1.5	1.5	0.1	0.05	1	10
F6	1	1.5	2	0.1	0.05	1	10
F7	1	2	1	0.1	0.05	1	10
F8	1	2	1.5	0.1	0.05	1	10
F9	1	2	2	0.1	0.05	1	10

3. Evaluation of Prepared Hydrogel Using Combination of Gelling Agent Under Study ^[13]

3.1 Appearance

The hydrogel formulated were observed or their visual appearance, colour, and feel upon application such as grittiness, grassiness, smoothness, stiffness and tackiness.

3.2 Spreadability

Spreadability is expressed in terms of time in seconds taken by two slides to slip off from gel and placed in between the slides under the direction of certain load, lesser the time taken for separation of two slides, better the Spreadability. It is calculated by using the formula

$$S = M \cdot L / T$$

Were,

M= weight tied to upper slide

L= length of glass slides

T= time taken to separate the slides

The results are shown in table no.4

3.3 pH

The pH was measured in each gel, using a pH meter, which was calibrated before each use with standard buffer solutions at pH 4, 7, 9. The electrode was inserted in to the sample 10 min priors to taking the reading at room temperature.

3.4 Viscosity

The viscosity of formulated hydrogel was determined using Brook-field viscometer (spindle number 7) Mounted the guard leg. Attached the spindle (left hand thread) to the viscometer lower shift by lifting the coupling screw slightly. It washed firmly with one hand while screwing the spindle on with the other (note left hand thread). Avoid spindle, do the following before attaching the spindle. Begin by immersing the spindle in a diagonal path, slowly drag the spindle across the fluid surface, and bring the spindle to an upright position and thread on to screw. Lower and centre spindle in the test material until the "meniscus" of the fluid is at the centre of the immersion groove on the spindle shaft. To make a viscosity measurement, turn the motor switch "ON". This energizes the viscometer drive motor. Allow time for the indicated reading to stabilize. The required for stabilization will depends on the speed at which the viscometer was running and the characteristics of the sample fluid. When making a viscosity measurement, the reading should be noted.

3.5 Drug Content Studies

To ensure uniform formulation of the gel, it was sampled from the different locations in the mixer and assayed for the drug content. Drug content of the gels was determined by dissolving an accurately weighed quantity of gel (about 1 gm) in about 100 ml of pH 7.4-phosphate buffer. These solutions were quantitatively transferred to volumetric flasks and appropriate dilutions were made with the same buffer solution. The resulting solutions were then filtered 0.45 mm membrane filters before subjecting the solution to Spectrophotometric analysis for Luliconazole at 296nm. Drug content was determined from the standard curve of Luliconazole

3.6 In-Vitro Release


The in vitro release experiments were carried out by using Franz-diffusion cells apparatus from different formulations. An exact number of formulations (1.0 g) was spread out on membrane positioned between the donor and receptor chambers with an available diffusion area. The receptor compartment was filled with phosphate buffer 7.4 and continuously stirred with a small magnetic bar at a speed of 50 rpm during the experiments to ensure homogeneity and maintained at 37.2 ± 0.5 °C. The samples were withdrawn at various time intervals and replaced with the same volume of PBS. Sink conditions were met in all cases. The samples were analysed Spectrophotometrically at 296nm

3.7 Kinetics of Drug Release

In vitro dissolution has been recognized as an important element in drug development. To analysis the mechanism for the release and release rate kinetics of the formulated dosage form, the data obtained from conducted studies was fitted into Zero order, First order, Higuchi matrix, Korsmeyer-Peppas and Hixson Crowell model. In this by comparing the R-values obtained, the best-fit model was selected.

4. Result and Discussion


4.1.a Determination of Lambda Max: m



Graph No 1. UV Spectrum of Luliconazole

Discussion: - The lambda max was found to be 296 nm in Phosphate buffer 7.4


4.1.b FTIR Spectroscopy Drug characterization study by FTIR was carried out as per standard procedure. FTIR spectra of Luliconazole are shown in graph No. 2. It was observed that principal peak of Drug was found in FTIR spectra of a drug. It was suggested that there was no physical and chemical change of pure.



Graph No 2. FTIR Spectrum of Luliconazole

Table No. 2 Functional groups and their frequencies with pure drug


Characteristics Peaks	Reported (cm ⁻¹)	Observation (cm ⁻¹)
C - H stretch	2850-3000	2937.59
C ≡ N stretch	2100-2400	2204.64
C ≡ C aromatic stretch	1450-1650	1556.55
C=C-C Aromatic Ring Stretch	1510-1450	1510.26
Para C-H distribution	860-800	854.47

**Graph No: - 3 FTIR Spectrum of Luliconazole and Polymers****Discussion: -**

Drug characterization study by FTIR was carried out as per standard procedure. FTIR spectra of Luliconazole and polymer mixture are shown in graph No. 3. It was observed that principal peak of Drug was found in FTIR spectra of a drug. It was suggested that there was no physical and chemical interaction is observed. The results are shown in Graph No.3

Table No. 3 Standard Calibration Curve of Luliconazole in Phosphate Buffer pH 7.4 at 296nm

Sr no	Concentration (ug/ml)	Absorbance
1	0	0
2	20	0.0361
3	30	0.0494
4	40	0.0639
5	50	0.0789



Graph No: - 4 Standard Calibration Curve of Luliconazole

Discussion:

From the standard curve, it was observed that the drug obeys Beer's law in concentration range of 2.0-15.0 µg/ml in phosphate buffer pH 7.4. The drug showed good linearity with a regression coefficient ($r^2=0.9961$) and the equation for this line obtained was found to be $y=0.0016x+0.0234$ which is used for the calculation of amount of drug and dissolution study.

4.2 Evaluation of Prepared Hydrogel

4.2.A Physical Appearance:

A prepared Evaluation of Prepared Luliconazole hydrogel was inspected visually for colour, homogeneity, consistency. All formulations showed white, white buff colour, appearance therefore showed suitable homogeneity and consistency. And the observations are mentioned in Table No. 4.

Table No 4. Physical Evaluation of Formulations


Formulation Code	colour	Feel of application	Spredability gm.cm/sec
F1	White	Smooth	12
F2	White	Smooth	11.30
F3	White	smooth	10.12
F4	White	Smooth	11.83
F5	White	smooth	10
F6	White	Smooth	9.65
F7	White	Smooth	9.81
F8	White	Smooth	9.11
F9	White	smooth	7

n=3


Table No: - 5 pH, Viscosity, and Drug Content

Formulation Code	pH	Viscosity(cp)	Drug content (%)
F1	6.5	3130	96.25
F2	6.7	3544	95.62
F3	6.7	4103	96.87
F4	6.3	3803	98.12
F5	6.8	4215	97.13
F6	6.5	5418	96.45
F7	6	7322	98.26
F8	6.9	8974	95.18
F9	6.7	10318	97.56

n=3


**Graph No 5: - Comparison of Spreadability of Factorial Batches****Discussion:**

The Spreadability of Topical Hydrogel formulation (F1 to F9) was found to be range 7-12. It was observed that Spreadability of the Hydrogel depends on the concentration of gelling agent Here, as concentration of gelling agent increases Spreadability decreases.

**Graph No 6: - Comparison of pH of factorial batches**

Discussion:


The pH of Topical Hydrogel formulations (F1 to F9) was found to be range 6 to 6.9. it was observed that pH of hydrogel depends upon concentration of preservatives.



Graph No 7: - Comparison of Viscosity of factorial batches

Discussion:

The Viscosity of Topical Hydrogel Factorial formulations (F1 to F9) was found to be range 3130 to 10318 cp. It was observed that viscosity of Hydrogel depends on concentration of polymer used for preparation of Hydrogel. Here, as concentration of polymers increases viscosity of formulation also increases.



Graph No 8: - Comparison of Drug Content of Factorial Batches


Discussion:

The % Drug content of Topical Hydrogel Factorial formulations (F1 to F9) was found to be range 95.18 to 98.26 it was observed that % drug content of Hydrogel depends on practical skill. Here, as the optimum % drug content be achieved by result reproducibility. can be achieved by result reproducibility.

Table No 5: In Vitro Drug Release of Factorial Batches F1-F9

Time (Hr)	F1	F2	F3	F4	F5	F6	F7	F8	F9
0	0	0	0	0	0	0	0	0	0
1	1.64	2	1.13	1.44	1.33	1.14	1.12	1.24	1.23
2	5.63	5.25	5	4.81	4.64	4.35	4.32	4.07	4.05
3	10.5	10.67	9.83	8.4	8.17	7.78	8.14	7.83	7.8
4	17.64	17.53	16.44	15.21	14.97	12.88	12.57	11.96	11.9
5	30.78	26.57	24.09	22.96	22.64	20.34	19.44	18.5	18.42
6	45.14	38.57	36.35	34.75	34.07	31.66	30.64	26.25	26.15
7	60.14	54.07	50.04	49.54	48.81	45.32	43.46	38.72	38.58
8	79.49	73.26	68.76	65.14	64.32	59.79	58.82	53.32	53.15

n=3



Graph No 9 Comparison of % Drug Release of Factorial Batches F1 to F9

Discussion:

The Cumulative % Drug Release of Topical Hydrogel of Factorial Batches (F1 to F9) was found to be range 53.15 (8 hours) to 79.49 (8 hours). It was observed that Cumulative % Drug Release of Hydrogels depends on concentration of Carbopol-934 and HPMC-K4M. Here, as concentration of Carbopol-934 and HPMC-K4M increases Drug release time of formulation also decreases. Maximum Drug Release i.e., 79.49 (8 hours) was found to be for F1, and prolong Cumulative % Drug Release 53.15 (8 hours) Found to be F9. Here, Carbopol-934, and HPMC-K4M shows concentration dependence release behaviour for these formulations.

Table No 6 Kinetic Model Studies of Factorial Batches

Kinetic Models	F1	F2	F3	F4	F5	F6	F7	F8	F9
	R	R	R	R	R	R	R	R	R
Zero order	0.9961	0.9982	0.8235	0.9991	0.9841	0.9985	0.9740	0.9979	0.8964
1 st order	0.9869	0.9954	0.9988	0.9125	0.9147	0.9974	0.9549	0.9912	0.9984
Matrix	0.9950	0.8987	0.9941	0.7928	0.9912	0.8245	0.9534	0.9869	0.9967
Peppas	0.9929	0.9964	0.8354	0.9963	0.9487	0.9874	0.9398	0.8459	0.9986
Hix.Crow	0.9919	0.9923	0.9945	0.8548	0.8945	0.9925	0.9722	0.9958	0.8794
Best fitted to	Zero order	Zero order	1 st order	Zero order	Matrix	Zero order	Zero order	Zero order	Peppas

n=3

It was observed that the Topical Hydrogels (F1-F2, F4, F6-F8) have best fitted to the Zero order model. Also, it was Observed that Topical Hydrogels (F3) formulations have best fitted to First order model. Batch (F5) Best suited for matrix model, Batch (F9) Best suited for peppas model, from above it was Concluded that Topical Hydrogel formulation F1 with R Value 0.9919, which follows Zero order kinetic, contains Carbopol-934 and HPMC-K4M 1% each and methyl paraben 0.1% and propyl paraben 0.05% which could be most Promising Topical Hydrogel formulation for Luliconazole.

Table No 7 Stability study for Factorial Batch F1 at 2-8^oC at Humidity 60 ± 05%

Duration Time	Drug Content (%)	% Drug Release	pH of Formulation
0	97.26	79.82	6.4
15	97.26	79.82	6.4
30	97.26	79.81	6.4
45	97.21	19.81	6.3

n=3

Table No 8 Stability study for Factorial Batch F1 at 25^oC at Humidity 64 ± 05%

Duration Time	Drug Content (%)	% Drug Release	pH of Formulation
0	97.26	79.82	6.4
15	97.22	79.78	6.3
30	97.22	79.77	6.1
45	97.19	97.74	6

n=3

Table No 9: Stability study for Factorial Batch F1 at 40°C at Humidity 54 ± 05%

Duration Time	Drug Content (%)	% Drug Release	pH of Formulation
0	97.26	79.82	6.4
15	96.86	79.77	6.3
30	96.17	79.75	6
45	95.93	97.72	5.9

Discussion: The stability study of optimum batch (F1) revealed that there is slightly reduction in drug content was observed over period of 45 days. No significant change was Observed in % drug content. The release condition depends upon the temp and duration of period. Drug release (after 8 Hrs) at various storing condition 2-8°C, 25°C, and 40°C Hence formulation was found to be stable for 45 days.

Conclusion: -

The topical hydrogel of Luliconazole was prepared using different concentration of gelling agent such as Carbopol-934 and HPMC-K4M, and prepared hydrogel were evaluated for various parameters such as Appearance, spreadability, PH, Viscosity, Drug Content, and Drug Release All the results are within limit, further, optimized formulation was studied for stability and formulation was found to be stable. due to its high retention, and rapid absorption from the skin it can be used successfully for the treatment of fungal infections.

Acknowledgement: -

I am thankful to Dr. Nishan N. Bobade sir, Associate Professor Vidyabharati College of pharmacy, Amravati for providing necessary guidance. I Would Also Like to Thank Virupaksha Organic Limited, Hyderabad for Providing Gift Sample of Luliconazole.

References

1. T Praveen Kumar,1 M Chinna Eswaraiah. Formulation and evaluation of topical hydrogel containing antifungal drug Pharmacy & Pharmacology International Journal. Volume 8 Issue 4 – 2020
2. Enas MA. Hydrogel: Preparation, Characterization and Applications: A Review. Journal of Advanced Research. 2013;6(2):106–121.
3. Kumar TG, Kaur LP. Formulation and Evaluation of Topical Gel of Aceclofenac. Journal of Drug Delivery & Therapeutics. 2013;3(6):51–53.
4. A. Salomy Monica, And J. Gautami Design and Evaluation of Topical Hydrogel Formulation of Diclofenac Sodium for Improved Therapy International Journal of Pharmaceutical Sciences and Research Ijpsr, 2014; Vol. 5(5): 1973-80.
5. E. M. Ahmed, —Hydrogel: Preparation, characterization, and applications: A review. Journal of advanced research, 2015; 6(2): 105–121
6. Vidya S, Sejal V. Formulation and Evaluation of Microemulsion-Based Hydrogel for Topical Delivery. International Journal of Pharmaceutical Investigation. 2012;2(3):140–149.
7. Deevan P, VothaniSB. Formulation and evaluation of liposomal gel containing antifungal activity Ketoconazole Indo American Journal of Pharmaceutical Research 2016; 6: 6154-6170
8. ShaileshT, Parthasarathi K. Liposomal Hydrogels: A novel drug delivery systems for wound dressing Current drug therapy 2012; 7: 212-218.

9. Shrimali H., Mandal U.K., Nivsarkar M., Shrivastava N. (2019); Fabrication and evaluation of a medicated hydrogel film with embelin from *Embelia ribes* for wound healing activity. "Future Journal of Pharmaceutical Sciences", 5(12): 1-10.
10. Sharma D., Sharma N., Roy B.G., Pathak M., Kumar V., Ojha H., (2021); Healing efficacy and dermal toxicity of topical silver nanoparticles-loaded hydrogel in Sprague-Dawley rats. "International Journal of Science and Research", 44(1): 34-41.
11. Avinash H, Hosmani, Thorat YS, Kasture PV. Carbopol and its pharmaceutical significance: A review Pharm Reviews 2006
12. Shishu, N. Aggarwal et al. Preparation of hydrogels of Griseofulvin for dermal application. International Journal of Pharmaceutics. 2006; 326; 20-24.
13. Vinita Singh et al. Design and evaluation of topical hydrogel formulation of Aceclofenac for improved therapy Journal of Drug Delivery & Therapeutics. 2019; 9(5); 118-122.
14. Chellam Pillai Bothiraja et al. Investigation of ethyl cellulose microsphere hydrogel for topical delivery of Eberconazole nitrate for fungal therapy. Journal of Therapeutic Delivery. 2014; 5(7); 781-

